

Tridonic
connection technology
GmbH & Co KG
Archenweg 58
6020 Innsbruck
Austria

Tel. +43 512 3321
Fax +43 512 3321-82
www.tridonic-ct.com

REACH DECLARATION

Innsbruck, 02 February 2012

SVHC Candidate List

On Dezember 19th, 2011 the European Chemicals Agency (ECHA) published the following list with Substances of Very High Concern (SVHC) on <http://echa.europa.eu>.

Zirconia Aluminosilicate Refractory Ceramic Fibres
Calcium arsenate
Bis(2-methoxyethyl) ether
Aluminosilicate Refractory Ceramic Fibres
Potassium hydroxyoctaoxodizincatedichromate
Lead dipicrate
N,N-dimethylacetamide
Arsenic acid
2-Methoxyaniline; o-Anisidine
Trilead diarsenate
1,2-dichloroethane
Pentazinc chromate octahydroxide
Formaldehyde, oligomeric reaction products with aniline
Bis(2-methoxyethyl) phthalate
4-(1,1,3,3-tetramethylbutyl)phenol
Lead diazide, Lead azide
Phenolphthalein
Dichromium tris(chromate)
Lead styphnate
2,2'-dichloro-4,4'-methylenedianiline
Cobalt dichloride
1,2,3-Trichloropropane
1,2-Benzenedicarboxylic acid, di-C7-11-branched and linear alkyl esters
1-Methyl-2-pyrrolidone
Hydrazine

Strontium chromate
 2-Ethoxyethyl acetate
 1,2-Benzenedicarboxylic acid, di-C6-8-branched alkyl esters, C7-rich
 Acids generated from chromium trioxide and their oligomers. Group containing: Chromic acid, Dichromic acid, Dichromic acid, Oligomers of chromic acid and dichromic acid
 Cobalt(II) carbonate
 Cobalt(II) diacetate
 2-Methoxyethanol
 Chromium trioxide
 Cobalt(II) dinitrate
 Cobalt(II) sulphate
 2-Ethoxyethanol
 Disodium tetraborate, anhydrous
 Ammonium dichromate
 Tetraboron disodium heptaoxide, hydrate
 Potassium dichromate
 Trichloroethylene
 Sodium chromate
 Potassium chromate
 Boric acid
 Acrylamide
 Lead chromate molybdate sulphate red (C.I. Pigment Red 104)
 Lead chromate
 Anthracene oil, anthracene-low
 2,4-Dinitrotoluene
 Anthracene oil, anthracene paste, anthracene fraction
 Anthracene oil
 Tris(2-chloroethyl)phosphate
 Aluminosilicate Refractory Ceramic Fibres
 Anthracene oil, anthracene paste, distn. lights
 Zirconia Aluminosilicate Refractory Ceramic Fibres
 Pitch, coal tar, high temp.
 Lead sulfochromate yellow (C.I. Pigment Yellow 34)
 Diisobutyl phthalate
 Anthracene oil, anthracene paste
 Sodium dichromate
 5-tert-butyl-2,4,6-trinitro-m-xylene (musk xylene)
 4,4'- Diaminodiphenylmethane (MDA)
 Bis(tributyltin)oxide (TBTO)
 Triethyl arsenate
 Dibutyl phthalate (DBP)
 Diarsenic trioxide
 Anthracene
 Alkanes, C10-13, chloro (Short Chain Chlorinated Paraffins)
 Lead hydrogen arsenate
 Benzyl butyl phthalate (BBP)
 Hexabromocyclododecane (HBCDD) and all major diastereoisomers identified: Alpha-hexabromocyclododecane
 Beta-hexabromocyclododecane Gamma-hexabromocyclododecane
 Diarsenic pentaoxide
 Bis (2-ethylhexyl)phthalate (DEHP)

We confirm that in the production process of Tridonic connection technology none of the substances recorded in the candidate list are intentionally added and that, according to our present knowledge, these substances do not exceed the maximum allowed weight percentage in any of our products.

With best regards



Reinhard Margreiter
Application engineering